

DATE:	February 12, 2026
PROJECT NO:	KM7830-03
PURPOSE:	Preliminary Cleaner Test.
PROCEDURE:	Perform a standard one product cleaner test.
FEED:	2 kg of American Antimony Sample #1 ground to a nominal 76µm K80.

KM7830-03 American Antimony Sample #1

Overall Metallurgical Balance

Product	Weight	Assay -	percent or g/tonne					Distribution - percent				
	%	grams	Sb	Fe	S	Au	Ag	Sb	Fe	S	Au	Ag
Bulk Con*	45.4	910.7	62.6	1.0	26.2	0.52	24	96.7	36.5	98.0	86.5	96.8
Bulk 1st Clnr Tail	3.9	77.3	11.6	2.9	3.54	0.30	4	1.5	9.0	1.1	4.2	1.4
Bulk Ro Tail	50.7	1016.8	1.05	1.3	0.20	0.05	0.4	1.8	54.5	0.8	9.3	1.8
Recalculated Feed	100.0	2004.8	29.4	1.2	12.1	0.27	11.3	100	100	100	100	100
Measured Feed	100.0		30.2	0.9	12.4	0.28	10.4					

KM7830-03 American Antimony Sample #1

Photos



KM7830-03 American Antimony Sample #1

Cumulative Metallurgical Balance

Cumulative Product	Cum. Weight	Assay -	percent or g/tonne					Distribution - percent				
	%	grams	Sb	Fe	S	Au	Ag	Sb	Fe	S	Au	Ag
Product 1	45.4	910.7	62.6	1.0	26.2	0.52	24	96.7	36.5	98.0	86.5	96.8
Product 1 to 2	49.3	988.0	58.6	1.1	24.4	0.50	22	98.2	45.5	99.2	90.7	98.2
Product 3	50.7	1016.8	1.05	1.3	0.20	0.05	0.4	1.8	54.5	0.8	9.3	1.8
Recalculated Feed	100.0	2004.8	29.42	1.2	12.1	0.27	11	100	100	100	100	100



Redacted for Proprietary Information